

# X-Pro® SP200 P 31608



## OVERVIEW

- Automotive certification: General Motors, GM-GMW16008
- Polypropylene Copolymer, recycled, medium flow
- Low cost alternative to virgin resin with comparable quality and process ability

## Processing

Injection Molding

## Application

Automotive General Purpose, Automotive Wheel Housings

## Color

General Purpose Black

## Quality

- ISO 9001: 2015 registered
- IEC 17025: 2005 accredited laboratories
- COA on every lot

PROPERTY	VALUE	UNITS	TEST METHOD
Melt Flow	17-22	g/10 min	ASTM D1238 / ISO 1133
Izod Impact Notched @ 23° C	3.2	Ft lbs/in	ASTM 256 / ISO 180/A
Tensile @ Yield	2,500	psi	ASTM D638 / ISO 527-1/2
Flexural Modulus 0.05 in/min	110,000	psi	ASTM D790 / ISO 178

## GENERAL INJECTION MOLDING GUIDE

### Barrel Temperature

Rear: 360°F to 420°F  
Middle: 380°F to 440°F  
Front: 400°F to 420°F

### Nozzle Temperature

400°F to 420°F

### Melt Temperature

400°F to 440°F

### Mold Temperature

80°F to 140°F

### Molding Pressure

Boost: 500 to 1,500 psi  
Hold: 50 to 75% of Boost  
Back: 50 to 150 psi

### Screw Speed

Medium to Fast

### Clamp Force

2 to 2.5 tons per square inch part projected area

### Drying

2 to 4 hours at 180°F



IMPORTANT: The following supersedes buyer documents. Seller makes NO WARRANTY, REPRESENTATION OR CONDITION OF ANY KIND, EXPRESS OR IMPLIED (INCLUDING NO WARRANTY OF MERCHANTABILITY OR FITNESS OF THE GOODS FOR ANY USE CONTEMPLATED BY BUYER) concerning the Goods and none shall be implied by law. Final determination of the suitability of the Goods for the use contemplated by Buyer is the sole responsibility of Buyer, and Seller shall in no way be responsible for the suitability of the Goods for any particular end use.